

Resistance to Chemical Reagents

MONARFLEX LDPE Products

The resistance list is categorized in 3 different levels:

S = Satisfactory

L = Limited

NS = Not Satisfactory

Sat. sol. = Saturated aqueous solution

Sol. = Aqueous solution at a concentration of higher than 10%.

L and NS categories are likely, in practice, to occur diluted to such a degree that it does not affect the Geomembranes.

Chemical resistance is carried out on specimens not subjected to mechanical stress, in contact with fluids at 20°C and 60°C (70°F and 140°F).

Chemical or Product	Concentration	70°F 20°C	140°F 60°C	Chemical or Product	Concentration	70°F 20°C	140°F 60°C
Acetaldehyde	100%	L	NS	Chlorine, aqueous	Sat. sol.	NS	NS
Acetic acid	10%	S	S	Chloroacetic acid	Sol.	-	-
Acetic acid	60%	S	L	Chlorobenzene	100%	NS	NS
Acetic acid, glacial	Greater than 96%	L	NS	Chloroform	100%	NS	NS
Acetic anhydride	100%	L	NS	Chloromethane	100%	-	-
Acetone	100%	L	NS	Chloromethane, gas	100%	L	-
Adipic acid	Sat. sol.	S	S	Chromic acid	Sat. sol.	S	S
Allyl alcohol	100%	L	NS	Chromic acid	20%	-	-
Allyl alcohol	96%	-	-	Chromic acid	50%	-	-
Alums	Sol.	S	S	Citric acid	Sat. sol.	S	S
Aluminium chloride	Sat. sol.	S	S	Copper (II) chloride	Sat. sol.	S	S
Aluminium fluoride	Sat. sol.	S	S	Copper (II) fluoride	Sat. sol.	S	S
Aluminium sulphate	Sat. sol.	S	S	Copper (II) nitrate	Sat. sol.	S	S
Ammonia, dry gas	100%	S	S	Copper (II) sulphate	Sat. sol.	S	S
Ammonia, liquid	100%	L	L	Cresylic acid -			
Ammonia, aqueous	Dil. sol.	S	S	(methyl benzoic acid)	Sat. sol.	-	-
Ammonium chloride	Sat. Sol.	S	S	Crotonaldehyde	Sat. sol.	L	-
Ammonium fluoride	Sol.	S	-	Cyclohexanol	Sat. sol.	L	NS
Ammonium nitrate	Sat. sol.	S	S	Cyclohexanol	100%	-	-
Ammonium sulphate	Sat. sol.	S	S	Cyclohexanone	100%	NS	NS
Ammonium sulphide	Sol.	S	S				
Amyl acetate	100%	-	-	Decalin (decahydronaphethanlene)	100%	-	-
Amyl alcohol	100%	L	L	Developers (photographic)	Work Conc.	-	-
Amyl chloride	100%	NS	NS	Dextrin	Sol.	S	S
Aniline	100%	-	-	Diethyl-ether	100%	NS	NS
Antimony (III) chloride	90%	-	-	Dimethyl amine	100%	NS	NS
Antimony trichloride	Sol	S	S	Dioctyl phthalate	100%	L	NS
Aqua regia	HCl/HNO ₃ =3/1	NS	NS	Dioxan	100%	-	-
Arsenic acid	Sat. sol.	S	S				
				Ethanediol (ethylene glycol)	100%	S	S
Barium carbonate	Sat. sol.	S	S	Ethanol	40%	S	L
Barium chloride	Sat. sol.	S	S	Ethanol	96%	L	L
Barium hydroxide	Sat. sol.	S	S	Ethyl acetate	100%	L	NS
Barium sulphate	Sat. sol.	S	S				
Beer	-	S	S	Fluorine gas	100%	L	NS
Benzaldehyde	100%	L	NS	Florosilic acid	50%	S	S
Benzene	100%	NS	NS	Formaldehyde	40%	S	S
Benzoic acid	Sat. sol.	S	S	Formic acid	50%	-	-
Borax	Sat. sol.	S	S	Formic acid	From 98-100%	S	S
Boric acid	Sat. sol.	S	S	Furfuryl alcohol	100%	L	NS
Bromine, dry gas	100%	NS	NS				
Bromine, liquid	100%	NS	NS	Gasoline, petrol			
Butane, gas	100%	-	-	(aliphatic hydrocarbons)		L	NS
Butanol	100%	S	L	Glucose	Sat. sol.	S	S
Butyric acid	100%	L	L	Glycolic	100%	S	S
				Glycolic acid	30%	S	L
				Glycolic acid	Sol.	-	-
Calcium carbonate	Sat. sol.	S	S				
Calcium chlorate	Sat. sol.	S	S	Heplane	100%	NS	NS
Calcium chloride	Sat. sol.	S	S	Hydrobromic acid	50%	-	-
Calcium hydroxide	Sat. sol.	S	S	Hydrobromic acid	Up to 100%	S	S
Calcium hypochlorite	Sol.	S	S	Hydrochloric acid	Up to 36%	S	S
Calcium nitrate	Sat. sol.	S	S	Hydrochloric acid	Conc.	-	-
Calcium sulphate	Sat. sol.	S	S	Hydrochloric acid	10%	S	S
Calcium sulphide (hydro)	Sol.	S	S	Hydrocyanic acid	4%	S	S
Calcium sulphide	Dil. Sol.	-	-	Hydrofluoric acid	60%	S	L
Carbon dioxide, dry gas	100%	-	-	Hydrogen	100%	S	S
Carbon dioxide, wet	-	S	S	Hydrogen peroxide	30%	S	L
Carbon disulphide	100%	NS	NS	Hydrogen peroxide	90%	S	NS
Carbon monoxide	100%	S	S	Hydrogen sulphide gas	100%	S	S
Carbon tetrachloride	100%	NS	NS	Hydroquinone	Sat. sol.	S	S
Chlorine, dry gas	100%	NS	NS				

Chemical or Product	Concentration	70°F 20°C	140°F 60°C	Chemical or Product	Concentration	70°F 20°C	140°F 60°C
Iron (III) chloride	Sat. sol.	S	S	Quinol (hydroquinone)	Sat. sol.	S	S
Iron (III) nitrate	Sol.	S	S	Salicylic acid	Sat. sol.	S	S
Iron (III) sulphate	Sat. sol.	S	S	Silver acetate	Sat. sol.	S	S
Iron (II) chloride	Sat. sol.	S	S	Silver cyanide	Sat. sol.	S	S
Iron (II) sulphate	Sat. sol.	S	S	Silver nitrate	Sat. sol.	S	S
Lactic acid	100%	S	S	Sodium benzoate	Sat. sol.	S	S
Lead acetate	Sat. sol.	S	S	Sodium bromide	Sat. sol.	S	S
Magnesium carbonate	Sat. sol.	S	S	Sodium carbonate	Sat. sol.	S	S
Magnesium chloride	Sat. sol.	S	S	Sodium chlorate	Sat. sol.	S	S
Magnesium hydroxide	Sat. sol.	S	S	Sodium chloride	Sat. sol.	S	S
Magnesium nitrate	Sat. sol.	S	S	Sodium cyanide	Sat. sol.	S	S
Maleic acid	Sat. sol.	S	S	Sodium fluoride	Sat. sol.	S	S
Mercury (II) chloride	Sat. sol.	S	S	Sodium hexacyanoferrate (III)	Sat. sol.	-	-
Mercury (II) cyanide	Sat. sol.	S	S	Sodium hexacyanoferrate (II)	Sat. sol.	-	-
Mercury (I) nitrate	Sol.	S	S	Sodium hydrogen carbonate	Sat. sol.	S	S
Mercury	100%	S	S	Sodium hydrogen sulphite	Sol.	S	S
Milk		S	S	Sodium hydroxide	40%	S	S
Mineral oils		S	S	Sodium hydroxide	Sol.	-	-
Molasses	Work conc.	S	S	Sodium hypochlorite	15%	-	-
Nickel chloride	Sat. sol.	S	S	available C1	-	-	S
Nickel nitrate	Sat. sol.	S	S	Sodium nitrate	Sat. sol.	S	S
Nickel sulphate	Sat. sol.	S	S	Sodium nitrite	Sat. sol.	S	S
Nicotinic acid	Dil. sol.	L	L	Sodium orthophosphate	Sat. sol.	S	S
Nitric acid	25%	S	S	Sodium sulphate	Sat. sol.	S	S
Nitric acid	50%	-	-	Sodium sulphide	Sat. sol.	S	S
Nitric acid	From 50 to 75%	L	NS	Sodium sulphite	Sat. sol.	S	S
Nitric acid	75%	-	-	Stearic acid	Sat. sol.	S	L
Nitric acid	100%	NS	NS	Sulphur dioxide, dry	100%	S	S
Oil and fats		L	NS	Sulphur trioxide	100%	NS	NS
Oleic acid	100%	L	NS	Sulphur acid	From 10 to 50%	S	S
Orthophosphoric acid	50%	S	S	Sulphuric acid	10%	-	-
Orthophosphoric acid	95%	S	L	Sulphuric acid	50%	-	-
Oxalic acid	Sat. sol.	S	S	Sulphuric acid	98%	L	NS
Oxygen	100%	S	-	Sulphuric acid	Fuming	NS	NS
Ozone	100%	NS	NS	Sulphurous acid	30%	S	S
Phenol	Sol.	L	S	Tannic acid	Sol.	S	S
Phosphoric (III) chloride	100%	S	S	Tartaric acid	Sat. sol.	S	S
Picric acid	Sat. sol.	S	L	Tartaric acid	Sol.	-	-
Potassium bromate	Sat. sol.	S	S	Thionyl chloride	100%	NS	NS
Potassium bromide	Sat. sol.	S	S	Tin (II) chloride	Sat. sol.	S	S
Potassium carbonate	Sat. sol.	S	S	Tin (IV) chloride	Sol.	S	S
Potassium chlorate	Sat. sol.	S	S	Tin (IV) chloride	Sat. sol.	-	-
Potassium chloride	Sat. sol.	S	S	Toluene	100%	NS	NS
Potassium chromate	Sat. sol.	S	S	Trichloroethylene	100%	NS	NS
Potassium cyanide	Sol.	S	S	Triethanolamine	100%	S	-
Potassium dichromate	Sat. sol.	S	S	Triethanolamine	Sol.	-	-
Potassium hexacyanoferrate (III)	Sat. sol.	S	S	Urea	Sol.	S	S
Potassium hexacyanoferrate (II)	Sat. sol.	S	S	Urine		S	S
Potassium fluoride	Sat. sol.	S	S	Vegetable oils		S	L
Potassium hydrogen carbonate	Sat. sol.	S	S	Vinegar		S	S
Potassium hydrogen sulphate	Sat. sol.	S	S	Water		S	S
Potassium hydrogen sulphite	Sol.	-	-	Wines and spirits		S	S
Potassium hydroxide	10%	S	S	Xylene	100%	NS	NS
Potassium hydroxide	Sol.	S	S	Yeast	Sol.	S	S
Potassium hypochlorite	Sol.	S	L	Zinc carbonate	Sat. sol.	-	-
Potassium nitrate	Sat. sol.	S	S	Zinc chloride	Sat. sol.	S	S
Potassium orthophosphate	Sat. sol.	S	S	Zinc oxide	Sat. sol.	S	S
Potassium perchlorate	Sat. sol.	S	S	Zinc sulphate	Sat. sol.	S	S
Potassium permanganate	20%	S	S				
Potassium persulphate	Sat. sol.	S	S				
Potassium sulphate	Sat. sol.	S	S				
Potassium sulphide	Sol.	S	S				
Potassium sulphite	Sat. sol.	S	S				
Propionic acid	50%	-	-				
Propionic acid	100%	-	-				
Pyridine	100%	-	-				

This information is not to be taken as a warranty for which we assume legal responsibility, nor as a permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, and verification. Products less than 10 mil may experience slightly lower resistance when exposed to very aggressive or abrasive chemical reagents.

Source, Extracts from Laboratory tests carried out by NESTE Chemicals.



Siplast 1000 E. Rochelle Blvd., Irving, TX 75062
Tel 469 995 2200, Fax 469 995 2249
In Canada: 201 Bewicke Avenue, Suite 210, North Vancouver, BC V7M 3M7
Tel 604 929 7687, Fax 604 929 7683
Toll Free in North America 1 800 922 8800 www.siplast.com